



Report

Certification of reference material

Poly(styrene) (PS)

Batch No.: **ps2088**

This material was produced by Polymer Standards Service GmbH (PSS), Mainz. It can be used for calibrating specific methods investigating polymers. Certified values are the mass averaged molecular weight M_w by means of light scattering (LS) and the intrinsic viscosity by means of viscometry. Additional, non-certified values are the averaged molecular weights (M_w , M_n , M_z , M_p) and M_w/M_n by means of size exclusion chromatography (SEC). These values are based on results obtained by round robin tests which were initiated and evaluated by the department BAM VI.3. Additional tests that result in non-certified values (IR, NMR, DSC, MFR and determination of density) were exclusively performed in the BAM.

Homogeneity and stability of the material were tested in the BAM, too.

This certificate is valid for five years after purchase. This validity may be extended as further evidence of stability becomes available.

Content:

	page
1) Abbreviation and symbols	3
2) Introduction	4
3) List of laboratories	5
4) Synthesis and packing size	6
5) Investigation of homogeneity	6
6) Investigation of stability	7
7) Non-certified values	8
8) Results of the round robin test	8
8.1) Size exclusion chromatography	8
8.2) Light scattering	9
8.3) Viscometry	9
9) References	10

1. Abbreviations, symbols and formulas

IR	-	infrared spectroscopy
NMR	-	nuclear magnetic resonance spectroscopy
DSC	-	differential scanning calorimetry
MFR	-	melt flow index
SEC	-	size exclusion chromatography
LS	-	light scattering
MALLS	-	multi-angle laser light scattering
LALLS	-	low-angle laser light scattering
MALDI-TOF-MS	-	matrix assisted laser desorption/ionisation - time of flight – mass spectrometry
M_w	-	weight averaged molecular weight
M_v	-	viscosity averaged molecular weight
M_p	-	molecular weight at peak maximum
M_n	-	number averaged molecular weight
M_z	-	z-averaged molecular weight
D	-	polydispersity (= M_w/M_n)
THF	-	tetrahydrofurane
\bar{x}	-	mean value
u_x	-	confidence interval of \bar{x}
σ	-	standard deviation of \bar{x}
$[\eta]$	-	intrinsic viscosity

$$M_n = \frac{\sum_{i=1}^k n_i * M_i}{\sum_{i=1}^n n_i} \quad (1)$$

$$M_w = \frac{\sum_{i=1}^k n_i * M_i^2}{\sum_{i=1}^n n * M_i} = \frac{\sum_{i=1}^k m_i * M_i}{\sum_{i=1}^k m_i} \quad (2)$$

$$M_z = \frac{\sum_{i=1}^k n_i * M_i^3}{\sum_{i=1}^n n * M_i^2} = \frac{\sum_{i=1}^k m_i * M_i^2}{\sum_{i=1}^k m_i * M_i} = \frac{\sum_{i=1}^k z_i * M_i}{\sum_{i=1}^k z_i} \quad (3)$$

2. Introduction

Polymer standards are the basis for calibration of relative methods used for the characterization of molecular weights and weight distribution of polymers. An important method is represented by the Size Exclusion Chromatography (SEC). The polymer, that has to be investigated, will be dissolved in an appropriate solvent and will be separated in columns according to the hydrodynamic radii of macromolecules. These columns are filled with specific gels having various pore sizes and pore distributions. The hydrodynamic volume depends both on the molecular weight and on the structure of dissolved polymers. Therefore, for analysing structurally different polymers various standards are necessary.

The molecular weight of these standards can be measured by means of so-called absolute methods, which do not require any calibration. One of the most important absolute methods is given by measuring the light scattering of a polymer solution. The intensity of the scattered light increases with increasing molecular weight. Apart from determining the refractive indices at different polymer concentrations (refractive index increment), no further information is necessary. For investigations carried out at the BAM a Dawn EOS light scattering photometer (Wyatt) was applied.

The SEC BAM round robin tests were performed and evaluated according to DIN 55 672 – 1. The conditions were obligatory for all participating laboratories. Samples were measured at the BAM using a PL-210 SEC (Polymer Laboratories, Church Stretton, UK). For the calibration of SEC commercially available standards were used (Polymer Standards Service [PSS] GmbH, Mainz) by all participating laboratories. The calculation of the molecular weights was performed using the WINGPC program of PSS, which is based on known mathematical formulas (1) to (3).

As a third method viscometry was used. The determination of the viscosities of polymer solutions with different concentrations and their subsequent extrapolation versus a concentration $c=0$ results in the so-called intrinsic viscosity $[\eta]$. Applying the equation $[\eta] = K M_v^a$ (K and a are constants available for different solvents and temperatures) a viscosity averaged molecular weight M_v can be obtained.

These investigations were performed in the BAM according to DIN 51562 – 1 using a AVS/G – Ubbelohde viscometer (Schott, Mainz).

3. List of participating laboratories

Aventis, Frankfurt / M.
Bundesanstalt für Materialforschung und -prüfung, Berlin
Bayer AG, Uerdingen
Bayer AG, Leverkusen
Bundeskriminalamt, Wiesbaden
BMW, Dingolfing
Fraunhofer Institut für Angewandte Polymerforschung, Teltow
RWTH Aachen, Institut für Kunststoffverarbeitung
Institut für Lacke und Farben, Magdeburg
Institut für Polymerforschung, Dresden
Martin-Luther-Universität, Halle-Wittenberg
Max-Planck-Institut für Polymerforschung, Mainz
Polymer Standards Service GmbH, Mainz
Röhm GmbH, Darmstadt
RWTH Aachen, Institut für Textilchemie und Makromolekularen Chemie
Goldschmidt AG, Essen
Technische Universität Dresden
Universität Bayreuth
Universität Erlangen-Nürnberg
Universität Essen
Universität Freiburg
Universität Hamburg, Institut für Technische und Makromolekulare Chemie
Universität Hamburg, Institut für Technische und Makromolekulare Chemie
Universität Leipzig
Johannes-Gutenberg-Universität Mainz, Institut für Makromolekulare Chemie
Johannes-Gutenberg-Universität Mainz, Institut für Physikalische Chemie
Universität Osnabrück
Universität Stuttgart, Institut für Technische Chemie
Universität Stuttgart, Institut für Textil- und Faserchemie
Universität Ulm
Universität - Gesamthochschule Siegen
Viscotek GmbH, Weingarten

4. Synthesis and packing size

The polymer was synthesized by Polymer Standards Service (PSS), Mainz. It was filled in 16 brown glass bottles with a volume of 1 litre. Each of these bottles contained ca. 210 g of the polymer. The polymers itself consist of a white amorphous material.

The samples were manually splitted. Every participant got approximately 2 grams of the polymeric material.

After certification a certain part of the whole polymer material will be bottled in sizes of 1, 2, 5 or 10 g by the distributor stating the corresponding batch number. The packing procedure will be controlled by the BAM. The remaining part of the material is stored in sealed bottles and can be packed by the distributor if required. The BAM reserves the right to check the packing procedure by taking samples immediately after packing and for an indefinite time.

5. Investigation of homogeneity

In order to separate the uncertainty of the method from the heterogeneity of the sample a multiple measuring of the sample according to ASTM E 826 – 85 is necessary. Since polymer materials are synthesized in batch processes and are repeatedly cleaned by various methods (e.g. re-precipitation) no significant differences were expected a priori.

Overall 16 samples of the polymer (one sample per bottle) were investigated by means of SEC. Every sample was measured twice.

$$M_w = 79500 \pm 360 \text{ g/mol } (\pm 0.45 \%)$$

(confidence interval for 32 values and 95% probability)

Additionally, the statistical accuracy of the SEC method was determined using a polystyrene standard material with a broad polymer distribution. One pellet of the polymer was dissolved in THF. This solution was measured 10 times.

$$M_w = 313300 \pm 400 \text{ g/mol } (\pm 0.14 \%)$$

(confidence interval for 10 values and 95% probability)

The confidence interval of the SEC method is lower than the confidence interval of the homogeneity test. (For comparison: The statistical accuracy of the SEC method according to DIN 55 672 – 1 has to be at least 2% for M_w .)

6. Investigation of stability

Stability tests were performed at elevated temperature (40 °C) by storing the polymers for two years. Samples were taken every six month. The molecular weight was determined twice by means of SEC.

Storage time (month)	Molecular weight M_w (g/mol)
0	79400
6	80500
12	80050
18	80060
24	79800

Only slight changes of 1,01 % (lower than the uncertainty of the SEC method) were detected within the timeframe. The results are within the statistical accuracy according to DIN 55 672 – 1.

7. Non-certified values

NMR-spectroscopy:	intensity ratio of aliphatic and aromatic protons: 3 / 5, no determination of end-groups
IR-Spectroscopy:	IR-spectrum corresponds with reference spectra
Differential Scanning Calorimetry:	glass transition temperature $T_g = 104.1$ °C
Melt Flow Index:	52 ± 0.9 g/10 min (5 kg, 200 °C, according to DIN ISO 1133)
Density:	1.04 g/ml (25 °C, according to DIN 53479)

8. Results of the round robin tests

Non-certified values

1. Averaged mol. weights (M_w , M_n , M_z and M_p) and polydispersity M_w/M_n by size exclusion chromatography (SEC)

Investigator	Mean values of investigators				
	Weight-average M_w [g/mol]	Number-average M_n [g/mol]	Z-average M_z [g/mol]	Mol. weight at peak max. M_p [g/mol]	M_w/M_n
1	76500	71300	80100	80750	1.07
2	79400	74050	82700	84000	1.07
3	83300	77400	87100	86500	1.08
4	80650	73700	86800	81750	1.09
5	78950	73400	82550	78350	1,08
6	75800	70050	79650	78900	1.08
7	79300	74650	82500	-	1.06
8	80200	73800	84400	82800	1.09
9	80400	76750	83400	83700	1.05
10	83050	77100	88000	86550	1.08
11	80600	75900	83600	84450	1.06
12	78850	74400	81300	-	1.06
13	78000	69000	84000	82500	1.13
Mean values	79600	74000	83600	82800	1.08
Confidence interval	± 1100	± 1300	± 1300	± 1300	± 0.01
[%]	1.33	1.72	1.50	1.60	0.92

Certified Values

2. Weight-average molecular weight (M_w) by light scattering (LS)

Investigator	Mean values of investigators
	Weight-average molecular weight M_w [g/mol]
1	89600 ^{a)}
2	89300 ^{b)}
3	89600 ^{b)}
4	95300 ^{a)}
5	80200 ^{b)}
6	89800 ^{c)}
7	80100 ^{b)}
8	85000 ^{b)}
9	86900 ^{a)}
10	98400 ^{b)}
11	79200 ^{c)}
12	88200 ^{b)}
13	87300 ^{c)}
14	86900 ^{d)}
Mean value	87600
Confidence interval	2245
[%]	2.91

3. Intrinsic viscosity by viscometry

Investigator	Mean values of investigators
	Intrinsic viscosity $[\eta]$ [ml/g]
1	42.13 ^{a,b)}
2	42.56 ^{a,b)}
3	43.02 ^{a,b)}
4	41.49 ^{a,b)}
5	42.76 ^{a,b)}
6	41.21 ^{c)}
7	40.70 ^{c)}
8	43.40 ^{c)}
Mean value	42.37
Confidence interval	± 0.83
[%]	1.96

Experimental conditions

- 1) The experimental conditions were determined by the DIN 55 672 – 1 (GPC using tetrahydrofurane (THF) as eluent).
- 2) Values correspond to a Rayleigh-ratio $R_{\theta} = 1.406 \text{ E-5 cm}^{-1}$ at 633 nm in toluene
 - a) Low-Angle Laser Light Scattering (LALLS).
 - b) Multi-Angle Laser Light Scattering (MALLS).
 - c) Size Exclusion Chromatography coupled with MALLS-Detector.
 - d) Size Exclusion Chromatography coupled with Right-Angle Laser Light Scattering (RALLS) – Detector

Investigator	Method	Angle (°)	Solvent	Equipment	Wave length (nm)	dn/dc
1	LALLS	6-7	THF	KMX-6	633	0.1844
2	MALLS	30-150	THF	Dawn EOS	690	0.1844
3	MALLS	30-150	Toluol	Dawn EOS	690	0.1096
4	LALLS	6-7	THF	KMX-6	633	0.1844
5	MALLS	30-150	THF	FICA(SLS)	633	0.1844
6	SEC-LS	30-145	THF	Dawn F	633	0.1844
7	MALLS	30-150	THF	Dawn DSP	488	0.1990
8	MALLS	30-145	Toluol	FIKA 50	633	0.1096
9	LALLS	6-7	THF	KMX-6	633	0.1844
10	MALLS	30-145	THF	Sofica	633	0.1844
11	SEC-LS	30-145	THF	DAWN F	633	0.1844
12	MALLS	90	Toluol	Sofica	633	0.1096
13	SEC-LS	30-145	THF	Dawn F	633	0.1844
14	SEC-LS	90	THF	TDA-300	633	0.1844

- 3) In THF at 30 °C. 6 concentrations from 1 to 5 g/l in an Ubbelohde type viscometer according to HUGGINS^{a)} and KRÄMER^{b)} following DIN 51562-1. resp. by means of a capillary viscometer (Viscotek. Weingarten)^{c)}

9. References

- DIN 55 672 – 1 (GPC using tetrahydrofurane (THF) as eluent)
- DIN 55 672 – 2 (GPC using N.N – Dimethylacetamide (DMAC) as eluent)
- DIN 51 562 – 1 (Viscometry: Determination of kinematic viscosity using a Ubbelohde – Viscometer. Part1: Design and realisation of measurements)
- BAM VI. 301 – standard working procedure (StAA 7.2.5.1.) (GPC using THF as eluent)
- BAM VI. 301 - StAA 7.2.5.2. (determination of the molecular weight of polymers using LALLS (Low-Angle Laser Light Scattering))
- BAM VI. 301 - StAA 7.2.5.3. (determination of the viscosity of polymers)